Valley Flash

LeakBarrier® ValleyFlash™

LeakBarrier ValleyFlash is a unique and highly versatile glass fiber reinforced sheet sandwiched between two layers of a heavy coating of superior quality bituminous resins modified with synthetic resins. Due to its remarkable characteristics, ValleyFlash meets the physical requirements of the ASTM D-1970 Moisture Vapor Permeability Test.

Usage

LeakBarrier ValleyFlash is designed for use under composition shingles, shake applications, all types of tile, and metal roofing.

Features and Benefits

- Technologically advanced valley liner
- Self sealing around nails
- Superior pliability of specially formulated SBS asphalt facilitates a flat laying sheet
- More cost-effective and easier to work with than metal
- Lays flat and resists wrinkling for ease of application
- Factory controlled characteristics
- Surpasses ATSM D-226 Type I & II standards
- Meets ASTM D-1970 Moisture Vapor Permeability Test standards



Storage

LeakBarrier ValleyFlash requires protection from damage and the weather. Constantly store rolls upright, in a dry location and never install when wet.

Application

- All roofing materials must be kept clean and free of moisture prior to installation.
- Deck must be clean, dry and free of voids.

Properties

Property	Typical Value	Reference Test
Approximate Thickness	55 Mils	ASTM D-5147
Tensile Strength (lbf/in.)	MD=45, CD=45	ASTM D-6163 Type 1
Tear Strength	Pass	ASTM D-6163 Type 1
Dimensional Stability	Pass	ASTM D-6163 Type 1
Pliability at 77°F	Pass	ASTM D-4601
Liquid Water Transmission Test	Pass	ASTM D-4869
Moisture Vapor Permeability	0.1 U.S. Perm or less	ASTM D-1970



Product Data

1Sq Roll

Roll Width 36 Inches
Roll Length 33.4 Ft.
Coverage per Roll 100 Sq. Ft.
Approximate Roll Weight 33 Lbs.
Rolls per Pallet 49

Warranty

LeakBarrier ValleyFlash is warranted to be free from manufacturer's defects.

Note

All statements information and data given herein are believed to be accurate and reliable, but are presented without guaranty, warranty or responsibility of any kind, expressed or implied, except as may be indicated otherwise in this literature. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent.





